

1 (original): A low application temperature thermoplastic hot melt adhesive having a viscosity at 275°F of less than about 8,000 centipose, a yield stress of less than about 80 psi and a creep performance for a bond made through strand coating of less than about 15%.

2 (original): The adhesive of claim 1 which has a creep performance for a bond made through spiral coating of less than about 25%.

3 (original): The adhesive of claim 1 comprising an amount of an additive effective to lower viscosity, increase toughness, and increase tensile strength.

4 (original): The adhesive of claim 3 which has a creep performance for a bond made through spiral coating of less than about 25%.

5 (original): The adhesive of claim 1 or 2 which comprises from about 0.5 to about 55 wt % of a thermoplastic elastomer, from about 30 to about 90 wt % of a tackifying resin, from 0 to about 40 wt % of a diluent and from 0 to about 25 wt % of a wax.

6 (original): The adhesive of claim 3 or 4 which comprises from about 0.5 to about 55 wt % of a thermoplastic elastomer, from about 30 to about 90 wt % of a tackifying resin, from 0 to about 40 wt % of a diluent, from 0 to about 25 wt % of a wax and up to about 40 wt % of said additive.

7 (original): The adhesive of claim 6 wherein said additive is an ionomer resin.

8 (currently amended): The adhesive of claim 7 comprising from about 0.1 to about 40 wt % of said ionomer resin.

9 (currently amended): The adhesive of claim 8 comprising from about 0.1 to about 15 wt % of said ionomer resin.

10 (original): The adhesive of claim 9 wherein the thermoplastic elastomer is styrene-isoprene-styrene, styrene-butadiene-styrene, styrene-b-ethylene/butylene-b-styrene or a mixture thereof.

11 (original): An article of manufacture comprising the adhesive of any one of claims 1 to 4.

12 (original): The article of claim 11 which is a disposable absorbent article.

13 (original): The article of claim 12 which is a disposable elastic article.

14 (original): The article of claim 13 which is a diaper.

15 (original): The article of claim 11 wherein the article of manufacture further comprises an elastomeric fiber selected from the group consisting of natural rubber, synthetic rubber, spandex, and melt-spun elastomers.

16 (original): The article of claim 15 wherein the adhesive comprises from about 0.5 to about 55 wt % of a thermoplastic elastomer, from about 30 to about 90 wt % of a tackifying resin, from 0 to about 40 wt % of a diluent, from 0 to about 25 wt % of a wax and up to about 40 wt % of an additive.